



Ventofiller Light

Product Description

Ventofiller Light is a two component, very low density epoxy based putty. It is the best choice for profiling above and below the waterline. Resistance to humidity and physical stress is excellent.

Intended Uses

It is used in the construction of new boats or for repairing old boats.

Physical Properties

Physical State	: Putty
Colour (Mixture)	: Grey
Volume Solid (%)	: 100
Density	: 0,60 ± 0,05 kg/L
Flexibility	: Good

Application Data

Mixing Ratio (weight)	: 1 unit Part A / 1 unit Part B
Application Methods	: Spatula, trowel.
Application Conditions	: The temperature of the substrate should be minimum 3°C above the dew point of the air. Good ventilation is required. It is not recommended to apply putty when the air temperature is below 10 °C.
Thinner/Cleaner	: Not advised.
Application Notes	: It is recommended not to exceed 1 cm thickness at one time.

Surface Preparations

All surfaces to be coated should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Primer

In the construction of a new boat, a suitable primer should be applied according to the surface and putty should be applied on it.

Coated surface

After applying 60-100 grade paper on the epoxy putty applied surface, suitable primer and then putty can be applied. Please contact Moravia office for further information.

Moravia	TECHNICAL DATA SHEET	Document No / Rev.	TBF 097 / 01
		Date	20.03.2023
		Page No	2 / 2

Drying Time

Substrate Temperature	Pot Life (max)	Sandable (min)
10°C	4 hrs	48 hrs
23°C	1,5 hrs	24 hrs
30°C	1 hour	16 hrs

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Packing Size : 15 L

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated area and away from source of heat and ignition. Containers must be kept tightly closed.

Health and Safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

Disclaimer: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.